



Registered Data Sheet Perforating System Evaluation, API RP 19B Section 1

API Form 19B-Section 1  Conforms to All Requirements of Section 1  Special Test - See Remarks/Exceptions below

Service Company Available to all from Titan Specialties Ltd. Explosive weight 12 gm, HMX powder, Case Material Steel

Gun OD & Trade Name 2-1/2" RTG Gun, 6 SPF 60 Degree Max Temp, °F 400 1 hr 3 hr 24 hr 100 hr 200 hr

Charge Name 2-1/2" 12 Gm HMX GH Maximum Pressure Rating 20,000 psi, Carrier Material H.T. Steel

Manufacturer Charge Part No. RTG-2512-431 Date of Manufacture 17 Aug 2010 Shot Density Tested 6 Shots/ft 6

Gun Type Hollow Steel Carrier, Expendable (HC, E) Recommended Minimum ID for Running 2.71 in.

Phasing Tested 60 degrees, Firing Order:  Top down  Bottom up Available Firing Mode:  Selective  Simultaneous

Debris Description Small steel chips, usually retained in carrier Debris Weight n/a gm/charge, Debris n/a in<sup>3</sup>/charge

Remarks/Exceptions per Section 1.11 \_\_\_\_\_

Casing Data 3-1/2" OD, Weight 9.2 lb/ft, API Grade, L-80 Date of Section 1 Test 30 Sept 2010

Target Data 54" OD, Amount of Cement 2,895 lb, Amount of Sand 5,790 lb, Amount of Water 1,508 lb.

Date of Compressive Strength Test 30 Sept 2010 Briquette Compressive Strength 6,710 psi, Age of Target 28 days

Shot No.	No 1	No 2	No 3	No 4	No 5	No 6	No 7	No 8	No 9	No 10	No 11
Clearance, in.	0.00	0.11	0.35	0.49	0.35	0.11	0.00	0.11	0.35	0.49	0.35
Casing Hole Diameter, Short Axis, in	0.42	0.42	0.44	0.45	0.46	0.44	0.42	0.43	0.43	0.45	0.45
Casing Hole Diameter, Long Axis, in	0.46	0.44	0.44	0.47	0.48	0.46	0.46	0.44	0.44	0.47	0.46
Average Casing Hole Diameter, in.	0.44	0.43	0.44	0.46	0.47	0.45	0.44	0.44	0.44	0.46	0.46
Total Depth, in.	19.75	18.50	19.50	22.63	23.88	18.75	19.25	21.25	19.75	19.38	22.75
Burr Height, in.	0.05	0.04	0.03	0.06	0.05	0.03	0.03	0.05	0.05	0.05	0.04

  

Shot No.	No 12	No 13	No 14	No 15	No 16	No 17	No 18	No 19	No 20	No 21	No 22	Average
Clearance, in.	0.11	0.00	0.11	0.35	0.49	0.35	0.11	0.00	0.11	0.35	0.49	XXXXXX
Casing Hole Diameter, Short Axis, in	0.46	0.43	0.42	0.42	0.46	0.46	0.42	0.42	0.42	0.42	0.45	0.44
Casing Hole Diameter, Long Axis, in	0.46	0.45	0.44	0.44	0.48	0.48	0.44	0.43	0.44	0.44	0.49	0.45
Average Casing Hole Diameter, in.	0.46	0.44	0.43	0.43	0.47	0.47	0.43	0.43	0.43	0.43	0.47	0.45
Total Depth, in.	19.75	18.00	19.75	20.50	21.13	24.25	19.75	21.00	20.25	19.75	17.75	20.31
Burr Height, in.	0.07	0.05	0.08	0.05	0.06	0.06	0.04	0.05	0.08	0.07	0.06	0.05

Remarks \_\_\_\_\_

Manufacturer's Certification

Type of Certification:  Self  Third Party

I certify that these tests were made according to the procedures as outlined in API 19B: Recommended Practice for Evaluation of Well Perforators, Second Edition, September 2006. All of the equipment used in these tests, such as the guns, jet charges detonator cord, etc., was standard equipment with our company for the use in the gun being tested and was not changed in any manner for the test. Furthermore, the equipment was chosen at random from stock and therefore will be substantially the same as the equipment that would be furnished to perforate a well for any operator. API neither endorses these tests nor recommends the use of the perforator system described.

CERTIFIED BY Kenneth B. Babcock CEO 08 Oct 2010 Titan Specialties Ltd. 143 HCR 4361, Milford, TX 76670

RECERTIFIED (Company Official) (Title) (Date) (Company) (Address)

Name of test as it should appear on website: 2.50-in. RTG 6 SPF w/ GH RTG-2512-431

Name of test as it appears on application and application date: \_\_\_\_\_



Registered Data Sheet Perforating System Evaluation, API RP 19B Section 1

Service Company Available to all from Titan Specialties Ltd. Explosive weight 12 gm, HMX powder, Case Material Steel  
 Gun OD & Trade Name 2-1/2" RTG Gun, 6 SPF 60 Degree Max Temp, °F 400 1 hr 3 hr 24 hr 100 hr 200 hr  
 Charge Name 2-1/2" 12 Gm HMX GH Maximum Pressure Rating 20,000 psi, Carrier Material H.T. Steel  
 Manufacturer Charge Part No. RTG-2512-431 Date of Manufacture 17 Aug 2010 Shot Density Tested 6 Shots/ft 6  
 Gun Type Hollow Steel Carrier, Expendable (HC, E) Recommended Minimum ID for Running 2.71 in.  
 Phasing Tested 60 degrees, Firing Order:  Top down  Bottom up Available Firing Mode:  Selective  Simultaneous  
 Debris Description Small steel chips, usually retained in carrier Debris Weight n/a gm/charge, Debris n/a in<sup>3</sup>/charge

Remarks/Exceptions per Section 1.11 \_\_\_\_\_

Casing Data 3-1/2" OD, Weight 9.2 lb/ft, API Grade, L-80 Date of Section 1 Test 30 Sept 2010  
 Target Data 54" OD, Amount of Cement 2,895 lb, Amount of Sand 5,790 lb, Amount of Water 1,508 lb.  
 Date of Compressive Strength Test 30 Sept 2010 Briquette Compressive Strength 6,710 psi, Age of Target 28 days

Shot No.	No 23	No 24	No 25	No 26	No 27	No 28	No 29	No 30	No 31	No 32	No 33	
Clearance, in.	0.35	0.11										
Casing Hole Diameter, Short Axis, in	0.44	0.44										
Casing Hole Diameter, Long Axis, in	0.45	0.44										
Average Casing Hole Diameter, in.	0.45	0.44										
Total Depth, in.	21.25	19.00										
Burr Height, in.	0.05	0.04										
Shot No.	No 34	No 35	No 36	No 37	No 38	No 39	No 40	No 41	No 42	No 43	No 44	Average
Clearance, in.												XXXXXXX
Casing Hole Diameter, Short Axis, in												0.44
Casing Hole Diameter, Long Axis, in												0.45
Average Casing Hole Diameter, in.												0.45
Total Depth, in.												20.31
Burr Height, in.												0.05

Remarks \_\_\_\_\_

Manufacturer's Certification

Type of Certification:  Self  Third Party

I certify that these tests were made according to the procedures as outlined in API 19B: Recommended Practice for Evaluation of Well Perforators, Second Edition, September 2006. All of the equipment used in these tests, such as the guns, jet charges detonator cord, etc., was standard equipment with our company for the use in the gun being tested and was not changed in any manner for the test. Furthermore, the equipment was chosen at random from stock and therefore will be substantially the same as the equipment that would be furnished to perforate a well for any operator. API neither endorses these tests nor recommends the use of the perforator system described.

CERTIFIED BY Kenneth B. Babcock CEO 08 Oct 2010 Titan Specialties Ltd. 143 HCR 4361, Milford, TX 76670  
 RECERTIFIED (Company Official) (Title) (Date) (Company) (Address)

Name of test as it should appear on website: 2.50-in. RTG 6 SPF w/ GH RTG-2512-431

Name of test as it appears on application and application date: \_\_\_\_\_